

# Pigmentation Table

## Bautech CREATIVO™

### 1) Polymer pigmentation (polymer + pigment)

Color		
	Component mixing	
	Polymer (g)	Pigment (g)
CRE 01 GREY	1000	7,5
CRE 02 LIGHT GREY	1000	3,9
CRE 03 NATURAL	1000	15,0
CRE 04 BASALT	1000	214,3
CRE 05 RED	1000	100,0
CRE 06 CREAM	1000	-
CRE 08 GRAPHITE	1000	100,0
CRE 10 YELLOW	1000	100,0
CRE 12 GREY CONCRETE	1000	30,0
CRE 13 BROWN	1000	100,0
CRE 14 GREEN	1000	100,0
CRE 15 BLUE	1000	357,1



### 2) Powder pigmentation (powder + pigmented polymer)

Color	Creativo BASE		Creativo FINISH		SUPER FINISH, FINE FINISH	
	BASE Powder	Pigmented Polymer	FINISH Powder	Pigmented Polymer	SUPER FINISH FINE FINISH powder	Pigmented Polymer
	Mixing ratio		Mixing ratio		Mixing ratio	
	(g)	(g)	(g)	(g)	(g)	(g)
CRE 01 GREY	1000	335,50	1000	403,00	1000	483,60
CRE 02 LIGHT GREY	1000	334,30	1000	401,55	1000	481,86
CRE 03 NATURAL	1000	338,00	1000	406,00	1000	487,20
CRE 04 BASALT	1000	340,00	1000	412,85	1000	495,42
CRE 05 RED	1000	330,00	1000	396,00	1000	475,20
CRE 06 CREAM	1000	-	1000	-	1000	-
CRE 08 GRAPHITE	1000	330,00	1000	396,00	1000	475,20
CRE 10 YELLOW	1000	330,00	1000	396,00	1000	475,20
CRE 12 GREY CONCRETE	1000	343,00	1000	412,00	1000	494,40
CRE 13 BROWN	1000	330,00	1000	396,00	1000	475,20
CRE 14 GREEN	1000	330,00	1000	396,00	1000	475,20
CRE 15 BLUE	1000	380,00	1000	461,40	1000	553,68